

**FORCE  
INDUSTRIES  
DIVISION**

American Solder & Flux Co., Inc. □ 28 Industrial Boulevard □ Paoli, PA 19301-0947 □ (610) 647-3575 □ FAX (610) 647-2375

---

## **PRODUCT INFORMATION**

### **AMCO M-9-C**

(199)

#### **High Temperature Silver Brazing Flux**

#### **General Characteristics and Uses**

*Amco M-9-C* is a silver brazing flux designed for extended heating times or temperature through the use of metallic boron additive. This smooth, creamy paste provides excellent results when used with most ferrous and non-ferrous metals, in any combination. Commonly used in torch, furnace and induction applications at a range of 1050° F to 1600° F. Proven performance with stainless steel, tungsten, copper, brass, bronze, steel and iron, among others. The flux belongs to AWS Brazing Class - Type FB3C and AMS 3411.

#### **Physical Data**

- Smooth, black paste
- Specific gravity: 1.55 - 1.65 @ 72 F
- pH: 7 - 7.5

#### **Performance Criteria**

- Residue - easily removed while hot, use water
- Superior wetting and dispersing action
- Completely cleans surface while protecting from re-oxidation during heating
- Will retard discoloration of braze area if temperature is uniform
- Not to be used with aluminum or aluminum alloys

#### **Storage and Handling**

- Ready for use as received
- Shelf life: one year in un-opened container. Keep from freezing
- Packaging: 1 and 5 lbs jars  
25 and 50 lb pails

While we believe the data presented herein is accurate and reliable, the data are not to be taken as a guarantee representation of any kind for which Force Industries assumes legal responsibility. They are offered solely for your consideration, investigation and verification.