

**FORCE
INDUSTRIES
DIVISION**

American Solder & Flux Co., Inc. □ 28 Industrial Boulevard □ Paoli, PA 19301-0947 □ (610) 647-3575 □ FAX (610) 647-2375

PRODUCT INFORMATION

AMCO 69

(592)

ALUMINUM SOLDERING FLUX

GENERAL CHARACTERISTICS AND USES.

AMCO 69 is a chloride free, organic flux especially formulated for low temperature, 350°F to 550° F (177°C to 288°C) soft soldering of aluminum. It is designed specially for joining aluminum to aluminum and aluminum to copper wire and cable in the electrical industry. The recommended solder for use with Amco 69 flux is 807, basically a Pb-Bi solder with small amounts of Ag and Sn.

PHYSICAL DATA

- Clear to hazy, amber colored, viscous liquid.
- Specific Gravity: 1.31 @ 70 °F
- Weight per gallon: 10.07 lbs
- Working Temp. 350°F to 550 °F
- pH 9.0 - 10.5
- Shelf Life At least one year in the unopened original and undamaged container stored temperatures below 100°F. Keep from freezing.

APPLICATION

- Use as is or dilute with ethyl alcohol. Dilution ratio depends on operating conditions and must be established accordingly.
- Used in high volume soldering of incandescent lamp bases.

RESIDUE

- The active ingredients may be decomposed under the soldering temperature but may leave slightly corrosive products. If desired, the residue may be removed with water or alcohol.

PACKAGING

- 5-gallon jugs
- 55-gallon drums

While we believe the data presented herein is accurate and reliable, the data are not to be taken as a guarantee or representation of any kind for which Force Industries assumes legal responsibility. They are offered solely for your consideration, investigation and verification.